



3120 / 4120 & Tissue Natural Rubber

Typical Physical Properties

PROPERTY	TEST METHOD	SPECIFICATION
Density (Average), lb/ft ³	ASTM D1056	26
Thickness, inches (Tolerance)	ASTM D1056	0.040 - 0.187 (± 0.015) 0.188 - 0.374 (± 0.030) 0.375 - 0.499 (± 0.040) 0.500 - 1.000 (± 0.060)
Standard Color, 3120 4120	-	Black Tan
Polymer	-	Natural Rubber
Compression Deflection, psi	ASTM D1056 at 25% Compression	5 - 10
Compression Deflection Change After Oven Aging, %	ASTM D1056 168 hrs at 158°F (70°C)	± 20
Compression Set, % max.	ASTM D395 50% Deflection at 158°F (70°C)	15
Temperature Range, °F	-	-20 to 160
Substrate	-	Cellulosic Tissue

Data reported is for the rubber only.

NOTES: Information of a technical nature is based on laboratory tests which either GRISWOLD PRODUCTS LLC conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. GRISWOLD PRODUCTS LLC believes these to be reliable. However, GRISWOLD PRODUCTS LLC has no control over the application of the material to, or part of, the final **product** and **therefore**, GRISWOLD PRODUCTS LLC makes **no express or implied warranty of result, fitness or merchantability**. The customer should determine reliability for the end use or particular application.

4/10/2023

One River Street, Moosup, CT 06354 USA
mechanicalrubber.com/griswoldproducts +1-800-472-8788
orders@griswoldproducts.com